

**PRODUCT DESCRIPTION** A three pack, silicone elastomer foul release coating.

**INTENDED USES** As the finishing coat in the Intersleek 737/757 foul release system (731/757 in North America). Especially designed for Deep Sea scheduled ships.  
For use at Newbuilding or Maintenance & Repair.

<b>PRODUCT INFORMATION</b>	<b>Colour</b>	BXA752-Blue (Part A), BXA755-Black (Part A), BXA756-Red (Part A), BXA757-Gray (Part A)
	<b>Finish/Sheen</b>	Gloss
	<b>Converter/Curing Agent</b>	BXA758 (Part B) and BXA759 (Part C)
	<b>Volume Solids</b>	72% ±2% (ISO 3233:1998)
	<b>Mix Ratio</b>	15 volumes Part A to 4 volumes Part B to 1 volume Part C
	<b>Typical Film Thickness</b>	150 microns dry (208 microns wet)
	<b>Theoretical Coverage</b>	4.80 (m <sup>2</sup> /lt) at 150 microns dft, allow appropriate loss factors
	<b>Method of Application</b>	Airless Spray, Brush, Roller
	<b>Flash Point</b>	Part A 31°C ; Part B 25°C ; Part C 32°C ; Mixed 23°C (Product produced and supplied in North America has flash points of Part A 38°C (100°F), Part B 25°C (77°F), Part C 35°C (95°F) and Mixed 29°C (84°F) respectively due to locally sourced solvents. There is no detrimental effect on product performance.)
	<b>Induction Period</b>	Not required

### Drying Information

	10°C	15°C	25°C	35°C
Touch Dry [ISO 1517:73]	8hrs	6hrs	3hrs	60mins
Hard Dry [ISO 9117:90]	10hrs	8hrs	5hrs	2hrs
Before Flooding	48hrs	43hrs	34hrs	24hrs
<b>Pot Life</b>	135mins	100mins	60mins	30mins

### Overcoating Data - see limitations

Overcoated By	Substrate Temperature							
	10°C		15°C		25°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max

**Note:** May be overcoated by self, either when fresh or after prolonged immersion provided surface is in good, clean condition. Consult International Paint.

<b>REGULATORY DATA</b>	<b>VOC</b>	254 g/lt as supplied (EPA Method 24) 241 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC)
		<b>This product does not contain organotin compounds acting as biocides and as such is in compliance with the International Convention on the Control of Harmful Anti-fouling Systems on ships as adopted by IMO in October 2001 (IMO document AFS/CONF/26).</b>

## CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Product recognised by the following classification societies as compliant with the International Convention on the Control of Harmful Anti-fouling Systems on Ships, 2001 (AFS 2001):  
Lloyds Register, Germanischer Lloyd, Korean Register of Shipping, DNV

Consult your International Paint representative for details.

---

## SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected.

---

## SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

Intersleek 757 must always be applied over Intersleek 737 tie coat (Intersleek 731 tie coat in USA) within the required overcoating interval.

Consult International Paint for detailed application advice and recommendations.

## APPLICATION

<b>Mixing</b>	Material is supplied in 3 containers as a unit. Always mix a complete unit in the proportions supplied. (1) Agitate Part A with a power agitator. (2) Combine entire contents of Part A and Part B and mix thoroughly with a power agitator. (3) Add entire contents of Part C and mix thoroughly with a power agitator. Once the unit has been mixed, it must be used within the working pot life specified.
<b>Thinner</b>	Not recommended. Use International GTA007 only in exceptional circumstances (max 5% by volume). DO NOT thin more than allowed by local environmental legislation.
<b>Airless Spray</b>	Recommended. - Tip range 0.38 - 0.53mm (15-21 thou) - Total output fluid pressure at spray tip not less than 211 kg/cm <sup>2</sup> (3000 p.s.i.)
<b>Conventional Spray</b>	Application by conventional spray is not recommended.
<b>Brush</b>	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. Consult International Paint.
<b>Roller</b>	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness. Consult International Paint.
<b>Cleaner</b>	International GTA822 or GTA007 (USA)
<b>Work Stoppages and Cleanup</b>	Do not allow material to remain in hoses, guns or spray equipment. Thoroughly flush all equipment with International GTA822 or GTA007 (USA). Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA822 or GTA007 (USA). It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
<b>Welding</b>	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

## SAFETY

**All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**  
**Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.**  
**EMERGENCY CONTACT NUMBERS:**  
USA/Canada - Medical Advisory Number 1-800-854-6813  
Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191  
R.O.W. - Contact Regional Office (see page 4 of Data Sheet)

### LIMITATIONS

Curing temperature must be above 10°C (50°F) and Relative Humidity above 40% otherwise film properties may be adversely affected.

Care should be taken to avoid overspray onto other coated areas.

Intersleek 757 must be applied over Intersleek 737 tie coat (Intersleek 731 tie coat in USA) within the required overcoating interval.

All equipment must be thoroughly clean prior to use, and before re-use with other materials, to prevent contamination. Liquid cleaners for Intersleek 757 must not be allowed to contaminate other paints.

Precautions should be taken to prevent silicone contamination of adjacent areas.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C (5°F) above the dew point. For optimum application properties bring the material to 21-27°C (70-80°F), unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

### UNIT SIZE

10 litre unit : Intersleek 757, Part A, 7.5 litres in a 10 litre container, Part B, 2.0 litres in a 2.5 litre container and Part C, 0.5 litres in a 0.75 litre container.

2.5 US gallon unit: Intersleek 757, Part A, 1.88 US gallons in a 2.5 US gallon container, Part B, 0.5 US gallons in a 0.5 US gallon container and Part C, 0.125 US gallons in a 1 US pint container.

*For availability of other unit sizes consult International Paint.*

### UNIT SHIPPING WEIGHT

10 litre unit: 12.10 kg

2.5 US gallon unit : 24.0 lb (10.9 kg)

### STORAGE

Shelf Life

24 months minimum at temperatures up to 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.


12 months minimum at temperatures greater than 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

### WORLDWIDE AVAILABILITY

Consult International Paint.

### IMPORTANT NOTE

*The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

 International and product names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

© Akzo Nobel, 2004

## Worldwide Operations

Argentina, Australia, Bahrain, Belgium, Brazil, Bulgaria, Canada, Chile, Colombia, Croatia, Cuba, Cyprus, Denmark, Ecuador, Egypt, Estonia, Fiji, Finland, France, Germany, Greece, Hong Kong, Iceland, India, Indonesia, Iran, Italy, Japan, Kuwait, Latvia, Lithuania, Luxembourg, Malaysia, Malta, Mexico, Netherlands, New Zealand, Northern Ireland, Norway, Pakistan, Panama, Papua New Guinea, Peoples Republic of China, Peru, Philippines, Poland, Portugal, Qatar, Republic of Ireland, Romania, Russia, Saudi Arabia, Singapore, Slovenia, South Africa, South Korea, Spain, Sri Lanka, Sweden, Taiwan, Thailand, Turkey, U.S.A., Ukraine, United Arab Emirates, United Kingdom, Uruguay, Venezuela, Vietnam, Western Samoa, Yemen

### Head Office

International Paint Ltd, Oriel House, 16 Connaught Place, London W2 2ZB, United Kingdom, Tel: +44 (0) 207 479 6000, Fax: +44 (0) 207 479 6500

[www.international-marine.com](http://www.international-marine.com)